



# Effect of Temperature on the Radial Distribution Function of Atoms in the Silicate Glass $2\text{SiO}_2\text{-PbO}$

M. E. Tursunov <sup>a\*</sup>, A. T. Dekhkanov <sup>a</sup>  
and G. Abdurakhmanov <sup>a</sup>

<sup>a</sup> National University of Uzbekistan Named After Mirzo Ulugbek, Tashkent, Uzbekistan.

## Authors' contributions

This work was carried out in collaboration among all authors. Author MET designed the study, performed the statistical analysis, wrote the protocol, and wrote the first draft of the manuscript. Author GA managed the analyses of the study. Author ATD managed the literature searches. All authors read and approved the final manuscript.

## Article Information

DOI: 10.9734/PSIJ/2023/v27i6805

## Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/107690>

Short Research Article

Received: 25/08/2023  
Accepted: 19/10/2023  
Published: 18/11/2023

## ABSTRACT

In this article, results of investigation of the effect of temperature on radial distribution function of atoms in lead-silicate glass are reported. Radial distribution functions of atoms in the lead-silicate glass  $2\text{SiO}_2\text{-PbO}$  were calculated via Mathematica 5.1 Wolfram Research from high-temperature X-ray diffraction patterns. It turned out that in the range of 773-973 K mainly variations of the location of atoms in the third coordination sphere have observed, while in the range of 973-1123 K, changes in the first and second coordination spheres take place.

**Keywords:** Temperature dependence of resistivity; thermopower coefficient; high-temperature X-ray diffraction; coordination spheres.

\*Corresponding author: E-mail: [muhridintursunov.1995@mail.ru](mailto:muhridintursunov.1995@mail.ru);

## 1. INTRODUCTION

In doped lead-silicate glass, at temperatures higher than 700 K, a sharp increase in resistivity  $\rho$  and thermopower coefficient  $S$  was observed (Fig.1) [1]. Based on the assumption that these changes caused by the structural transitions of the glass itself and the nanocrystals present in it, these dependences in the range from the temperature of liquid helium to 1200 K was explained qualitatively [2].

However, there was no direct experimental basis for this assumption, since the nanocrystals in the glass are very small (1-2 nm in size), so it is not possible to determine the changes in their structure directly (for example, using X-ray diffraction).

It is known that when studying the structure of non-crystalline substances by diffraction methods, only the radial distribution function  $\rho(r)$  of its atoms can be determined [3,4]. Here  $r$  is the distance from the central atom to other atoms [5]. In essence, heavy atoms play the main role in X-ray diffraction [6]. The meaning of  $\rho(r)$  is that the  $4\pi r^2 \rho(r) dr$  is number of atoms located on spherical layer of radius from  $r$  to  $r + dr$  centered at given (heavy) atom. Here,  $4\pi r^2$  is the surface of a sphere with a radius  $r$ ,  $4\pi r^2 dr$  is the volume of a spherical layer of thickness  $dr$  on the surface of this sphere.

For the radial distribution function, calculations using Fourier transforms give the following formula [7]:

$$4\pi r^2 \rho(r) = 4\pi r^2 \rho_0 + \frac{2r}{\pi} \int_0^\infty s \left\{ \frac{I(s)}{Nf^2} - 1 \right\} \sin sr ds. \quad (1)$$

Here  $\rho_0 = \rho(r \rightarrow \infty)$ ,  $I(s)$  is the intensity distribution in the X-ray diffraction image,  $s = (2\pi \sin \theta) / \lambda$  is the change of the X-ray wave vector during the scattering process,  $N$  is the number of atoms in the studied substance,  $f$  is the shape coefficient of atoms. Formula (1) gives the average value of the spatial radial distribution of atoms in space and time. If the studied sample consists of several types of atoms, then formula (1) has the following form:

$$\sum_m 4\pi r^2 \rho_m(r) = \sum_m k_m 4\pi r^2 \rho_0 + \frac{2r}{\pi} \int_0^\infty s \left\{ \frac{I(s)}{\sum_m f_m^2} - 1 \right\} \sin sr ds. \quad (2)$$

In this case,  $k_m$  is the effective number of X-ray scattering electrons in a  $m$ -type atom, often determined by the  $k_m$ -type atomic shape coefficient  $f_m$  graph. This method is universal and applies to all types of isotropic substances, only for amorphous substances it is necessary to subtract the intensity of incoherent scattering from the experimentally obtained ( $s$ ). Above, the presence of nanocrystals in lead-silicate glass and the physical basis of studying structural transitions in them using X-ray diffraction in the range of 300-1123 K were assumed. In order to test these assumptions in practice, X-ray diffraction images of the sample in the range of 300-1123 K have obtained and atomic arrangement has studied.

It should be noted that in all silicates, including vitreous silicate glasses silicon atoms are surrounded by oxygen atoms in  $[\text{SiO}_4]^{4-}$  tetrahedra (Fig. 2), which are connected to each other and another atoms only through their ends [8].

## 2. MATERIALS AND METHODS

Lead silicate glass was fired in a furnace at 1123 K for 60 minutes. The finished glass was turned into powder-like particles with a diameter of 0.2-0.5  $\mu\text{m}$  in a grinder. X-ray patterns of silicate glass at temperatures of 293, 773, 973 and 1123 K (Fig. 3) were skiagraphed on a Siemens D500 X-ray diffractometer with the Anton Parker HTK16N high-temperature chamber. The temperature points 293, 773, 973 and 1123 K were chosen for the experiment because at these points  $R(T)$  and  $S(T)$  (Fig. 1) start to increase sharply, reach a maximum and return almost to their initial values. One can see from Fig. 3, the X-ray diffraction images of the sample affected by temperature, but it is impossible to say variations on arrangement of which atoms led to these changes. Therefore, it is necessary to calculate the radial distribution function  $\rho(r)$  of atoms [9].

## 3. RESULTS AND DISCUSSION

The radial distribution functions of atoms calculated according to formula (1) are presented in Fig. 3.

It can be seen that the changes in the radial distribution function at 300 and 773 K (Fig. 3a) are hardly noticeable, that is, there was no change in the glass structure up to 773 K. The radial distribution function at 973 and 1123 K (Fig. 3b) differs from the previous one, especially

this difference is clearly visible in the maximum near 2.2 Å.

The radial distribution function was calculated for lead atoms [6]. Accordingly, structural transitions

in nanocrystals begin, reach a maximum, and end at these points. In this case, due to the increase in the distance between the atoms, the overlap of their wave functions decreases.




Fig. 1. Temperature dependences of resistance  $R$  and coefficient of thermopower  $S$  in  $2SiO_2\text{-}PbO$  glass doped with  $RuO_2$  [1]




Fig. 2. Spatial arrangement of atoms in lead-silicate glass (model)





Fig. 3. X-ray scattering image of  $2SiO_2\text{-}PbO$  glass at different temperatures: 300 K (a), 773 K (b), 973 K (c) and 1123 K (d)



**Fig. 4. Radial distribution functions in 2SiO<sub>2</sub>-PbO glass at different temperatures: a) 293K and 773K, b) 973K and 1123K**

It is known Sidorov [10] that heavy atoms make the main contribution to X-ray diffraction in amorphous substances consisting of several types of atoms. Accordingly, in Fig. 4, the radial distribution functions are calculated starting from the heaviest atom in the glass - lead atoms, that is, these atoms are located at the beginning of the coordinates.

#### 4. CONCLUSION

It was detected that increasing the temperature up to 773 K causes small changes in third coordination sphere (maximum at 7 Å, arrangement of oxygen atoms beyond the silicon atoms), while change in the first (2.2 Å) and the second (4 Å) coordination spheres observed mainly at 973 and 1123 K, where nearest oxygen and silicon atoms displaced around lead atoms.

#### COMPETING INTERESTS

Authors have declared that no competing interests exist.

#### REFERENCES

1. Abdurakhmanov G, NG. Abdurakhmanova // Phys. Stat. Sol.(a). 2005;202(9):1799-1802.
2. Abdurakhmanov G. Features of the structure and transport properties of alkali-free lead silicate glasses doped with metal oxides. Author's abstract. diss. Doctor of Physics and Mathematics Sciences. Tashkent; 2014.
3. Kitaygorodsky AI. X-ray structural analysis of fine-crystalline and amorphous bodies. – Moscow-Leningrad, GITTL, 1952– 589.
4. Ojovan MI, DV. Louzguine-Luzgin // J Phys. Chem. B. 2020;124(15):3186- 3194.
5. Liu X, Hua D, Wang W, Zhou Q, Li S, Shi J, He Y, Wang H. Atomistic understanding of incipient plasticity in BCC refractory high entropy alloys. Journal of Alloys and Compounds. 2022;920:166058.
6. Sidorov TA. // Izv. Academy of Sciences of the USSR. Inorg. Materials – Moscow. 1967;3 (12):2235-2239
7. Kitaygorodsky AI. X-ray structural analysis of fine-crystalline and amorphous bodies, M.-L., GITTL. 1952;589.
8. Liebau F, Structural chemistry of silicates. Per. from English - M.: Mir. 1988;416c.
9. Nozaki T, Doyama M, Kogure Y, Yokotsuka T. Micromachining of pure silicon by molecular dynamics. Thin Solid Films. 1998;334(1-2):221-4.
10. Sidorov TA. Interpretation of the results of x-ray studies of silicate and borate glasses with heavy elements // Izv. Academy of Sciences of the USSR. Inorg. Mater - M. 1967;3(12):2235-2239.

© 2023 Tursunov et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:

<https://www.sdiarticle5.com/review-history/107690>