



# **Green synthesis and Characterization of Silver Nanoparticles Synthesized Using *Piper longum* and its Antioxidant Activity**

**Taanya Imtiaz<sup>a</sup>, R. Priyadharshini<sup>a#</sup>, S. Rajeshkumar<sup>b#</sup> and Palati Sinduja<sup>a#</sup>**

<sup>a</sup> Department of Pathology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, 160, Poonamallee High Road, Vellappanchavadi Chennai 77, India.

<sup>b</sup> Department of Pharmacology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, 160, Poonamallee High Road, Vellappanchavadi Chennai 77, Tamilnadu, India.

## **Authors' contributions**

*This work was carried out in collaboration among all authors. Author TI and SR prepared the Piper longum Ag nanoparticle solution and performed the DPPH assay to assess the anti-oxidant activity of Piper longum. The data collection was done by author TI. Author TI wrote the manuscript and it was edited and revised by author RP. Authors RP and SR approved the submission of the manuscript. All authors read and approved the final manuscript.*

## **Article Information**

DOI: 10.9734/JPRI/2021/v33i51A33501

### Editor(s):

(1) Sawadogo Wamtinga Richard, Ministry of Higher Education, Scientific Research and Innovation, Burkina Faso.

### Reviewers:

(1) Ajay Kumar Srivastava, ST Xavier's College, India.

(2) Marwa Yassien Badr, Tanta University, Egypt.

(3) Olena Grechana, Zaporizhzhya State Medical University, Ukraine.

Complete Peer review History, details of the editor(s), Reviewers and additional Reviewers are available here:

<https://www.sdiarticle5.com/review-history/77072>

**Original Research Article**

**Received 08 September 2021**

**Accepted 16 November 2021**

**Published 24 November 2021**

## **ABSTRACT**

**Background:** *Piper longum*, a traditional plant used for regenerative medicine commonly known as the long pepper, is used to treat many pathological conditions. *Piper longum* is used as a source for obtaining the production of various nanoparticles and testing their efficacy. *Piper longum* has many beneficial activities, such as antifungal, anti-amoebic, anti-asthmatic, anti-cancer, anti-oxidant, anti-inflammatory, antidepressants activities. Silver nanoparticles are widely and commonly used for its antimicrobial activity against various microorganisms. Our study aimed to synthesize *Piper longum* based silver nanoparticles and to investigate its anti-oxidant property.

# Assistant Professor;

\*Corresponding author: E-mail: priyadharshinir.sdc@saveetha.com;

**Materials and Methods:** *Piper longum* plant extract was prepared and silver nanoparticles extract was synthesized. DPPH assay was then performed to assess the free radical scavenging activity of the *Piper longum* silver nanoparticle extract. The further analysis was that the formation of brownish-red color observed was evident, resulting in the synthesis of silver nanoparticles.

**Results:** Brown discoloration represents formation of silver nanoparticles and the antioxidant activity was noted to be from 60% to 70% from 10 to 50 $\mu$ L. But when compared to standard vitamin C values the *Piper longum* silver nanoparticles showed less antioxidant activity.

**Conclusion:** The *Piper longum* mediated silver nanoparticles showed remarkable and considerable antioxidant activity but when compared with the standard sample values the antioxidant activity was low.

**Keywords:** Antioxidant; innovative technique; eco-friendly; green synthesis; *Piper longum*.

## 1. INTRODUCTION

*Piper longum*, a traditional plant used for regenerative medicine commonly known as the long pepper, is used to treat many pathological conditions [1]. Various substitutes that are derived from *Piper longum*, one of the most important derivatives, is piperine. It's used to treat diarrhea, chronic bronchitis, stomach pain, asthma, hepatitis, and other respiratory insufficiencies. Advanced technology implying the use of nanoparticles in biomedical research, is gaining its agenda, incorporating almost all natural materials as sources [2].

Drug delivery is the most common use of nanoparticles in the current technological application.

*Piper longum* is used as a source for obtaining the production of various nanoparticles and testing their efficacy. *Piper longum* possesses various pharmacologically beneficial activities, such as insecticide and acaricidal, anti-fungal, anti-amoebic, anti-asthmatic, anti-cancer, antioxidant, anti-inflammatory, antidepressants, antiulcer activities on routine consumption [3–5]. The fruit of the *Piper longum* has hepatoprotective activity [6].

It is considered as an ayurvedic medicine providing enough treating ability to boost up the immune system to fight against various pathological disorders. Piperlongumine, sesamin, and sylvatin are important phytoconstituents of *Piper longum* [7]. The chemical nature of these constituents is the ability to produce antioxidant activity. Nanoparticles are minute particles that range from 1 to 100 nm on a nanometer scale. Different nanoparticles possess different properties; they vary in physical and chemical nature.

Nanotechnology is now widely used for synthesizing drugs in the pharmaceutical industry. Formulation of nanoparticles, nanospheres, nano-capsules, nano-emulsion, and nanosuspensions are few applications of nanotechnology in the field of nanomedicine. The most common synthesized nanoparticles are plasmonic silver and gold because they possess unique physical and chemical properties when compared to other large surface areas and have strong electronic properties [8].

Nanoparticles are physically and chemically altered to have high potency to act upon the biological cell structure of the body [9,10]. Silver nanoparticles are widely and commonly used for the conduction of electricity [11]. They also have a localized resonance effect on the surface plasmon and have a wide range of antimicrobial activity against various microorganisms [12]. The synthesis of silver nanoparticles involves 3 complex methods, they include physical synthesis, chemical synthesis, and biological synthesis [13].

The most important method used to synthesize silver nanoparticles involves the chemical method because of the nature of the silver nanoparticles which have the ease to simply dissolve in the prepared aqueous solution [14]. Silver nanoparticles are commonly used in nanotechnology [15]. Antioxidant activity is generally stated as prevention of oxidation of various constituents of the body, thus substances that tend to possess antioxidant activity which will block the oxidation of protein, DNA, and lipids present in our body.

An antioxidant prevents the formation of free radicals and their storage in tissues thus helps to prevent tissue depletion [16,17]. Various naturally occurring plant sources and their products have antioxidant properties, which

depresses and overcomes the oxidative stress caused by free radicals [18]. The beneficial activities of *Piper longum* include antioxidant properties which have the ability to treat chronic conditions.

The aim of this study is to green synthesize and characterize the silver nanoparticles using *Piper longum* plant extract and to observe its antioxidant capacity.

## 2. MATERIALS AND METHODS

### 2.1 Preparation of Plant Extract

Commercially available dry powder of *Piper longum* was used for this experiment. This experiment was an in vitro study which was conducted in Saveetha Dental College, Chennai, Tamil Nadu. The experiment was carried out by dissolving 1g of *Piper longum* powder in 100ml of water. The mixture was then boiled in a heating mantle at 70 degrees Celsius for up to 10 minutes. The boiled mixture was then filtered using a Whatman number 1 filter paper to obtain the plant extract. Then 40 ml of plant extract was measured using a measuring cylinder and the mixture was added to 60ml of 1 mM silver nitrate (0.0169 g) dissolved in 60ml distilled water. The lab technician reconfirmed the synthesized *Piper longum* silver nanoparticles to avoid sampling error for further analysis. The further analysis was that the formation of brownish-red color observed was evident, resulting in the synthesis of silver nanoparticles.

### 2.2 Reagent and Chemicals

1g of *Piper longum* powder

1 mM silver nitrate (0.0169 g)

2-10µg/ml concentration of *Piper longum* extract at various concentrations (10µL, 20µL, 30µL, 40µL, and 50µL)

0.1 mM DPPH in methanol 50 mM of tris HCl buffer

Control: BHT: Butylated hydroxytoluene

### 2.3 Antioxidant Activity

*Piper longum* was the plant used to determine the antioxidant activity by taking only 5 samples

in distinct test tubes and adding 10µL, 20µL, 30µL, 40µL, and 50µL of the solution respectively using a micropipette. The micropipette usage was dealt with care to avoid methodology error. Random sampling method was performed to eliminate sampling bias and the validation of the procedure was done by principal investigator and by experts in nanotechnology. Other plants and activities were not tested in this present study.

To check the antioxidant activity, a DPPH assay was used to test the antioxidant activity of biogenic synthesized silver nitrate nanoparticles. Diverse concentrations (2-10µg/ml) of *Piper longum* leaf extract interceded silver nitrate nanoparticle was mixed with 1 ml of 0.1 mM DPPH in methanol and 450µl of 50mM of tris HCl buffer (pH7.4) and incubated for 30 minutes. Later, the reduction in the quantity of DPPH free radicals was assessed dependent on the absorbance at 517 nm. BHT was employed as control. The percentage of inhibition was determined from the following equation:

$$\% \text{ Inhibition} = \frac{\text{Absorbance of control} - \text{Absorbance of sample}}{\text{Absorbance of control}} \times 100$$

The percentage of inhibition was then calculated and correlated with the standard vitamin C concentration values which were not performed. And the antioxidant activity was correlated using Spearman's correlation in SPSS software version 23.0, the correlation graph was then represented and the p value was less than 0.05 for the non-parametric correlation analysis proving statistical significance.

## 3. RESULTS

The optical observation of the experiment was determined using a UV-visible spectrum providing the characterization of the prepared silver particles. The formation and synthesis of silver nanoparticles were determined by the brownish-yellow discoloration shown (Fig. 1). The corresponding formation of silver nanoparticles with peaks at 517nm in UV spectrophotometer graph (Fig. 4). The presence of the surface plasmon resonance was the reason for the color change of the solution.




Fig. 1. The color change indicates the synthesis of silver nanoparticles after 72hours and its corresponding correlation of the UV spectroscopy (Fig. 4)




Fig. 2. The UV/Visible spectrum of the silver nanoparticles synthesized using the *Piper longum* plant leaf extract




Fig. 3. Antioxidant activity of the silver nanoparticles using the plant extract and the colour change is noted

Silver nanoparticles were formed by the reaction between the plant extract and the silver ions. Only potential plants were able to synthesize nanoparticles thus the change in color of the solution acted as a primary identification tool. The DPPH assay performed to test the antioxidant activity of the synthesized *Piper longum* silver nanoparticles was shown (Fig. 2).


The percentage of inhibition of the synthesized *Piper longum* silver nanoparticles was noted to be 61.2%, 64.5%, 66.1%, 67.4% and 69.3% at 10µL, 20µL, 30µL, 40µL and 50µL respectively

and whereas the values of the standard vitamin C solution are 76.5%, 78.8%, 84.9%, 89.2% and 92.3% at 10µL, 20µL, 30µL, 40µL and 50µL respectively (Table 1). The correlation analysis performed using SPSS version 23.0 and was shown in (Fig. 5). There was a positive correlation between the concentration of the sample prepared and percentage of inhibition.


Thus, the antioxidant activity was increasing with increased concentration of the synthesized silver nanoparticles (Fig. 3).

**Table 1. The Percentage of Inhibition for the different concentrations of the silver nanoparticles (ranging from 10µL to 50µL) in comparison with the standard**

Percentage of Inhibition (%)		
Concentration (µL)	Silver nitrate nanoparticles	Standard
10µL	61.2%	76.5%
20µL	64.5%	78.8%
30µL	66.1%	84.9%
40µL	67.4%	89.2%
50µL	69.3%	92.3%



**Fig. 4. Antioxidant activity of silver nanoparticles. The X-axis represents the concentration of the silver nanoparticles and standard solution and the Y-axis represents the percentage of inhibition. Graph representing the percentage of inhibition observed with the different concentrations ranging from 10µL to 50µL in comparison to the standard value, the correlation was found to be positive using spearman's correlation. And the non-parametric correlation was found with P value less than .05 proving statistically significance**



**Fig. 5.** The line graph represents the comparative observation of the antioxidant activity of *Piper longum* AgNPs (blue) and the standard solution antioxidant activity (green). The X-axis represents the concentration of the silver nanoparticles and standard solution and the Y-axis represents the percentage of inhibition. The correlation was found to be positive using Spearman's correlation. And the non-parametric correlation was found with P value less than .05 proving statistically significance

#### 4. DISCUSSION

The present study investigated the optical observation which was the initial and novel technique that revealed the characterization of the synthesized silver nanoparticles as it presented a result of the UV- visible absorption spectra. The brownish-yellow discoloration indicated the formation of the silver nanoparticles. The silver nanoparticle formation showed significant color change because of the occurrence of the surface plasmon resonance [19-20]. As the color change served as a primary tool, this was useful in the detection of the potential plants for the synthesis of silver nanoparticles.

The color change in the prepared solution was correlated with its UV spectrophotometer graph, in which the peak of the synthesized *Piper longum* solution with silver nanoparticles production is 517 nm. Similar studies showed that the prepared nanoparticles accompanied with the respective natural plant components used in assessing its antioxidant activity [21-22].

The production of the chosen nanoparticles were formed at the range of 400-520 nm in a UV visible spectrophotometer graph [23]. So compatible values of the UV spectrophotometer graph revealed the silver nanoparticle produced in 48 hrs.

2,2-diphenyl-1-picrylhydrazyl is an organic chemical compound which stands as the full form of DPPH, it is an assay performed to determine the antioxidant that is the free radical scavenging activity of a substance [24]. So, the DPPH assay was performed to observe the antioxidant activity of the synthesized silver nanoparticles in this present study. A bar graph comparison represented the percentage of inhibition between the silver nanoparticles synthesized and the standard solution and a line graph version of the already displayed bar graph of the results were elicited.

In comparison to various works conducted by different authors, the study conducted by S.N Kharat et al., [25] the DPPH assay scavenging ability was in a purely dose-dependent manner,

the scavenging property at 50 $\mu$ L was 15.23% which was the lowest concentration whereas when compared to the present study the antioxidant activity was 61.2% at the lowest concentration that is at 10 $\mu$ L which represents a correlation analysis.

The work conducted by Rajeshkumar [19] also concluded that the free radical scavenging activity was concentration dependent as well. Keshari et al., [26] concluded in study that AgNPs had the scavenging property of more than 29% stating its high free radical scavenging activity. Comparing works of DPPH radical scavenging with the work done by Zdenka et al., [27] stated that the activity was more than 89% at the highest concentration being 50 $\mu$ L.

Opposing work conducted by Chaudhary SK et al., [28] without the involvement of nanoparticles showed that there was potential antioxidant activity exhibited by the synthesized *Piper longum* extract. The *Piper* species were accountable and known for their reduction of oxidative stress which made them a good source of an antioxidant substance. They were successfully used to treat Alzheimer's disease and Parkinson's disease which are common disorders affecting the central nervous system [29].

Generally the silver nanoparticles were remarkable for its significant antioxidant activity [30], they also showed numerous beneficial activities such as antimicrobial [31-32] and anti-inflammatory [33], so silver nanoparticles were most commonly used metal nanoparticles in nanomedicine [34]. So silver nanoparticles played a crucial role in nanomedicine involving nano technological advances and also for biomedicine using genetic engineering [35]. The use of silver nanoparticles made the present study economical, less cost effective, and easily available [36].

But not so on the bright side, recent researchers had found that silver nanoparticles consumption had caused some adverse effects on human metabolism. The toxic adverse effects included suppressing activity of the cell growth, division and multiplication [37], which was found to be in a pure concentration consumption and exposure manner.

The present study, was based on the silver nanoparticles having the property of possessing

equally accessible antioxidant activity when compared to the standard scavenging property of the vitamin C solution [38]. Vitamin C was chosen for this present study from the other two free radical scavenging vitamins that are A and E because of the slightly higher values of the antioxidant activities shown by them on various biomedical facilities [39].

Vitamin C free radical scavenging property is due to its capacity to donate an electron which provided the basic properties of a vitamin which was potent enough to show strong antioxidant activity. An antioxidant thus work by preventing the oxidation of the cells and tissues present in the human body and thereby neutralizing the free radicals produced [40]. Substances which possessed strong antioxidant activity had a great potential to treat and cure many highriskhuman metabolic problems like atherosclerosis and cardiovascular disorders [41]. In vitro studies have clearly ruled out the antioxidant activity of vitamin C in biological systems [42].

The present study, dealt with the comparison of the prepared *Piper longum* plant extract nanoparticles with standard Vitamin C values which showed significant values of free radical scavenging property. But the plant extract nanoparticle prepared had less antioxidant activity than the standard values. There were clear and accurate values of the antioxidant activity of the two solutions used to check its antioxidant activity.

Limitations of the present study, were less sample size taken for the study, different plants could be taken as they all showed different antioxidant capacity and other beneficial properties. Only antioxidant activity of the *Piper longum* plant was assessed, and the specification in using silver nanoparticles. Value changes may be formed due to errors in experiment performance.

According to the present study conducted, the free radical scavenging property of the prepared *Piper longum* plant extract silver nanoparticles was from an average range of 60% to 70% of the antioxidant activity. The maximum antioxidant activity was shown at the highest concentration that is at 50 $\mu$ L it showed nearly 70% of inhibition. Thus, the prepared *Piper longum* silver nanoparticles had good antioxidant activity and can be potentially used in nanomedicine to treat various biological conditions.

The future scope of this study, was the properties of synthesizing nanoparticles which were further implied in nanotechnology which may be useful for nanomedicine, biomedicine and other sourcing fields. Furthermore, research works were needed to potentiate the various aspects of the use of nanoparticles in different fields. Our team has extensive knowledge and research experience that has translate into high end publications [43-62].

## 5. CONCLUSION

The *Piper longum* mediated silver nanoparticles showed remarkable and considerable antioxidant activity when compared with the standard values of vitamin C. The potential free radical scavenging property of the plant leaves extract mediated silver nanoparticles, was applicable in nanomedicine through the help of advanced technologies to support the medical voided fields. The properties of the synthesized nanoparticles were further implied in nanotechnology which may be useful for other sourcing fields. Further research studies were required to assess the full potential of the plant mediated nanoparticles.

## CONSENT

It is not applicable.

## ETHICAL APPROVAL

It is not applicable.

## ACKNOWLEDGEMENTS

We would like to thank Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University for providing us support to conduct the study.

## COMPETING INTERESTS

Authors have declared that no competing interests exist.

## REFERENCES

1. Kumar S, Kamboj J, Suman. Overview for various aspects of the health benefits of *Piper longum* linn. fruit. J Acupunct Meridian Stud. 2011;4(2):134–40.
2. Khushbu C, Roshni S, Anar P. Phytochemical and therapeutic potential of *Piper longum* Linn a review. International journal of research in Ayurveda and pharmacy. 2011;2(1):157–61.
3. Zaveri M, Khandhar A, Patel S. Chemistry and pharmacology of *Piper longum* L. International journal of pharmaceutical sciences review and research. 2010;5(1):67–76.
4. Brundha MP. A comparative study-the role of skin and nerve biopsy in hansen's disease. Res J Pharm Biol Chem Sci. 2015;7(10):837.
5. Brundha MP, Pathmashri VP, Sundari S. Quantitative changes of red blood cells in cancer patients under palliative radiotherapy-a retrospective study. Research Journal of Pharmacy and Technology. 2019;12(2):687–92.
6. Jalalpure SS, Patil MB, Prakash NS. Hepatoprotective activity of the fruits of *piper longum* linn. Indian J Pharm Sci. 2003;65(4):363.
7. Reddy NJ, Nagoor Vali D, Rani M. Evaluation of antioxidant, antibacterial and cytotoxic effects of green synthesized silver nanoparticles by *Piper longum* fruit. Mater Sci Eng C Mater Biol Appl. 2014;34:115–22.
8. Alaqad K, Saleh TA. Gold and silver nanoparticles: Synthesis methods, characterization routes and applications towards drugs. J Environ Anal Toxicol [Internet]. 2016;6(4). Available: <http://dx.doi.org/10.4172/2161-0525.1000384>
9. Mendoza KC, McLane VD, Kim S. *In vitro* application of gold nanoprobe in live neurons for phenotypical classification, connectivity assessment, and electrophysiological recording. Brain Res. 2010;1325:19–27.
10. Timothy CN, Samyuktha PS, Brundha MP. Dental pulp stem cells in regenerative medicine--A literature review. Research Journal of Pharmacy and Technology. 2019;12(8):4052–6.
11. Chernousova S, Epple M. Silver as antibacterial agent: ion, nanoparticle, and metal. Angew Chem Int Ed Engl. 2013;52(6):1636–53.
12. Shen J, Shi M, Li N, et al. Facile synthesis and application of Ag-chemically converted graphene nano composite. Nano Res. 2010;3(5):339–49.
13. Rajeshkumar S, Malarkodi C. *In vitro* Antibacterial activity and mechanism of silver nanoparticles against foodborne



- pathogens. *Bioinorg Chem Appl.* 2014; 2014:581890.
14. Yu J, Zhou X. Synthesis of dendritic silver nanoparticles and their applications as SERS substrates. *advances in materials science and engineering [Internet];* 2013. [Cited 2021 Feb 15];2013. Available:<http://dx.doi.org/10.1155/2013/519294>
  15. Karthiga P, Rajeshkumar S, Annadurai G. Mechanism of larvicidal activity of antimicrobial silver nanoparticles synthesized using garcinia mangostana bark extract. *J Cluster Sci.* 2018;29(6):1233–41.
  16. McCune LM. Traditional medicinal plants of indigenous peoples of Canada and their antioxidant activity in relation to treatment of diabetes. *Bioactive Food as Dietary Interventions for Diabetes: Bioactive Foods in Chronic Disease States.* 2012;221.
  17. Harsha L, Brundha MP. Prevalence of dental developmental anomalies among men and women and its psychological effect in a given population. *Journal of Pharmaceutical Sciences and Research; Cuddalore.* 2017;9(6):869–73.
  18. Rajeshkumar S. Anticancer activity of eco-friendly gold nanoparticles against lung and liver cancer cells. *J Genet Eng Biotechnol.* 2016;14(1):195–202.
  19. Rajeshkumar S. Antioxidant activity of characterized silver nanoparticles synthesized using flower extracts of *Chrysanthemum indicum*. *Res J Biotechnol.* 2017;12(8):38–43.
  20. Rajeshkumar S, Bharath LV. Mechanism of plant-mediated synthesis of silver nanoparticles - A review on biomolecules involved, characterisation and antibacterial activity. *Chem Biol Interact.* 2017;273:219–27.
  21. Maillard M-N, Soum M-H, Boivin P. Antioxidant activity of barley and malt: Relationship with phenolic content. *LWT - Food Science and Technology.* 1996;29(3):238–44.
  22. Miliauskas G, van Beek TA, Venskutonis PR. Antioxidant activity of potentillafruticosa [Internet]. Vol. 84, *Journal of the Science of Food and Agriculture.* 2004;1997–2009. Available:<http://dx.doi.org/10.1002/jsfa.1914>
  23. Miller NJ, Rice-Evans CA. Spectrophotometric determination of antioxidant activity. *Redox Rep.* 1996; 2(3):161–71.
  24. Dizhbite T, Telysheva G, Jurkane V. Characterization of the radical scavenging activity of lignins—natural antioxidants. *Bioresour Technol.* 2004;95(3):309–17.
  25. Kharat SN, Mendhulkar VD. Synthesis, characterization and studies on antioxidant activity of silver nanoparticles using Elephantopus scaber leaf extract. *Materials Science and Engineering: C.* 2016;719–24.
  26. Keshari AK, Srivastava R, Singh P. Antioxidant and antibacterial activity of silver nanoparticles synthesized by *Cestrum nocturnum*. *J Ayurveda Integr Med.* 2020;11(1):37–44.
  27. Bedlovičová Z, Strapáč I, Baláž M. A brief overview on antioxidant activity determination of silver nanoparticles. *Molecules [Internet].* 2020;25(14). Available:<http://dx.doi.org/10.3390/molecules25143191>
  28. Chaudhary SK, Mukherjee PK, Maiti. Evaluation of Angiotensin converting enzyme inhibition and anti-oxidant activity of *Piper longum* L; 2013. Available:<http://nopr.niscair.res.in/handle/123456789/19446>
  29. Karthikeyan J, Rani P. Enzymatic and non-enzymatic antioxidants in selected Piper species. *Indian J Exp Biol.* 2002;41(2):135–40.
  30. Abou El-Nour KMM, Eftaiha A, Al-Warthan A. Synthesis and applications of silver nanoparticles. *Arabian Journal of Chemistry.* 2010;3(3):135–40.
  31. Rajeshkumar S. Phytochemical constituents of fucoidan (*Padina tetrastrum*) and its assisted AgNPs for enhanced antibacterial activity. *IET Nanobiotechnol.* 2017;11(3):292–9.
  32. Kundara R. Synthesis of silver nanoparticles by extract of neem (*Azadirachta*), Tulsi (*Ocimum Tenuiflorum*) and Mint (*Mentha*) Leaves Using; 2020.
  33. Mani AKM, Seethalakshmi S, Gopal V. Evaluation of in-vitro anti-inflammatory activity of silver nanoparticles synthesised using piper nigrum extract. *J Nanomed Nanotechnol.* 2015;6(2):1.
  34. Ankamwar B, Damle C, Ahmad A. Biosynthesis of gold and silver nanoparticles using *Emblica Officinalis* fruit extract, their phase transfer and transmetallation in an organic solution. *J Nanosci Nanotechnol.* 2005;5(10):1665–71.

35. Midha K, Singh G, Nagpal M. Potential application of silver nanoparticles in medicine. *Nanoscience & Nanotechnology-Asia*. 2016;6(2):82–91.
36. Ahmad N, Sharma S, Alam MK. Rapid synthesis of silver nanoparticles using dried medicinal plant of basil. *Colloids Surf B Biointerfaces*. 2010;81(1):81–6.
37. Parveen K, Banse V, Ledwani L. Green synthesis of nanoparticles: Their advantages and disadvantages. *AIP Conf Proc*. 2016;1724(1):020048.
38. Bosetti M, Massè A, Tobin E. Silver coated materials for external fixation devices: *In vitro* biocompatibility and genotoxicity. *Biomaterials*. 2002;23(3):887–92.
39. Padayatty SJ, Katz A, Wang Y. Vitamin C as an antioxidant: evaluation of its role in disease prevention. *J Am Coll Nutr*. 2003;22(1):18–35.
40. Mittal AK, Kaler A, Banerjee UC. free radical scavenging and antioxidant activity of silver nanoparticles synthesized from flower extract of rhododendron dauricum. *Nano Biomed Eng*. 2012;4(3).
41. Fotherby MD, Williams JC, Forster LA. Effect of vitamin C on ambulatory blood pressure and plasma lipids in older persons. *JHypertens*. 2000;18(4): 411–5.
42. Asard H, May J, Smirnoff N. Vitamin C: Its functions and biochemistry in animals and plants. Taylor & Francis. 2004;344.
43. Anita R, Paramasivam A, Priyadharsini JV. The m6A readers YTHDF1 and YTHDF3 aberrations associated with metastasis and predict poor prognosis in breast cancer patients. *Am J Cancer Res*. 2020 Aug1;10(8):2546–54.
44. JayaseelanVP, Paramasivam A. Emerging role of NET inhibitors in cardiovascular diseases. *Hypertens Res*. 2020;43(12): 1459–61.
45. Sivakumar S, SmilineGirija AS, Vijayashree Priyadharsini J. Evaluation of the inhibitory effect of caffeic acid and gallic acid on tetR and tetM efflux pumps mediating tetracycline resistance in *Streptococcus* sp., using computational approach. *Journal of King Saud University - Science*. 2020;32(1):904–9.
46. SmilineGirija AS. Delineating the immunodominant antigenic vaccine peptides against gacS-sensor kinase in *acinetobacter baumannii*: An in silico Investigational Approach. *Front Microbiol*. 2020;11:2078.
47. Iswarya JaisankarA, Smiline Girija AS, Gunasekaran S. Molecular characterisation of csgA gene among ESBL strains of *A. baumannii* and targeting with essential oil compounds from *Azadirachta indica*. *Journal of King Saud University - Science*. 2020;32(8):3380–7.
48. Girija ASS. Fox3+ CD25+ CD4+ T-regulatory cells may transform the nCoV's final destiny to CNS! *J Med Virol [Internet]*; 2020. Available:<http://dx.doi.org/10.1002/jmv.26482>
49. Jayaseelan VP, Ramesh A, Arumugam P. Breast cancer and DDT: putative interactions, associated gene alterations, and molecular pathways. *Environ Sci PollutRes Int*. 2021;28(21):27162–73.
50. Arumugam P, George R, Jayaseelan VP. Aberrations of m6A regulators are associated with tumorigenesis and metastasis in head and neck squamous cell carcinoma. *Arch Oral Biol*. 2021;122:105030.
51. Kumar SP, Girija ASS, Priyadharsini JV. Targeting NM23-H1-mediated inhibition of tumour metastasis in viral hepatitis with bioactive compounds from *Ganoderma lucidum*: A computational study. *pharmaceutical-sciences [Internet]*. 2020; 82(2). Available:<https://www.ijpsonline.com/article/s/targeting-nm23h1mediated-inhibition-of-tumour-metastasis-in-viral-hepatitis-with-bioactive-compounds-from-ganoderma-lucidum-a-comp-3883.html>
52. Girija SA, Priyadharsini JV, Paramasivam A. Prevalence of carbapenem-hydrolyzing OXA-type  $\beta$ -lactamases among *Acinetobacter baumannii* in patients with severe urinary tract infection. *Acta Microbiol Immunol Hung*. 2019;67(1):49–55.
53. Priyadharsini JV, Paramasivam A. RNA editors: Key regulators of viral response in cancer patients. *Epigenomics*. 2021;13(3): 165–7.
54. Mathivadani V, Smiline AS, Priyadharsini JV. Targeting Epstein-Barr virus nuclear antigen 1 (EBNA-1) with Murrayakoengii bio-compounds: An in-silico approach. *Acta Virol*. 2020;64(1):93–9.
55. Girija As S, Priyadharsini JV, AP. Prevalence of Acb and non-Acbcomplex in

- elderly population with urinary tractinfection (UTI). *Acta Clin Belg.* 2021; 76(2):106–12.
56. Anchana SR, Girija SAS, Gunasekaran S. Detection of *csgA* gene in carbapenem-resistant *Acinetobacter baumannii* strains and targeting with *Ocimum sanctum* biocompounds. *Iran J Basic Med Sci.* 2021;24(5):690–8.
57. Girija ASS, Shoba G, Priyadharsini JV. Accessing the T-Cell and B-Cell immunodominant peptides from *A. baumannii* Biofilm Associated Protein (*bap*) as Vaccine Candidates: A Computational Approach. *Int J Pept Res Ther.* 2021;27(1):37–45.
58. Arvind PTR, Jain RK. Skeletally anchored forsus fatigue resistant device for correction of Class II malocclusions-A systematic review and meta-analysis. *Orthod Craniofac Res.* 2021;24(1):52–61.
59. Venugopal A, Vaid N, Bowman SJ. Outstanding, yet redundant? After all, you may be another Choluteca Bridge! *Semin Orthod.* 2021;27(1):53–6.
60. Ramadurai N, Gurunathan D, Samuel AV. Effectiveness of 2% Articaine as an anesthetic agent in children: randomized controlled trial. *Clin Oral Investig.* 2019;23(9):3543–50.
61. Varghese SS, Ramesh A, Veeraiyan DN. Blended module-based teaching in biostatistics and research methodology: A retrospective study with postgraduate dental students. *J Dent Educ.* 2019; 83(4):445–50.
62. Mathew MG, Samuel SR, Soni AJ. Evaluation of adhesion of *Streptococcus mutans*, plaque accumulation on zirconia and stainless steel crowns, and surrounding gingival inflammation in primary molars: randomized controlled trial [Internet]. *Clinical Oral Investigations.* 2020;24:3275–80. Available:<http://dx.doi.org/10.1007/s00784-020-03204-9>

© 2021 Imtiaz et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

*Peer-review history:*

The peer review history for this paper can be accessed here:  
<https://www.sdiarticle5.com/review-history/77072>